

TECHNICAL DATA SHEET Scheda Tecnica

09/02/2023

Design Offset Natural White

Characteristic	Standard	Unit	80g	90g	100g	120g	160g	250g	300g	Tolleranza/ Tolerance
Grammage / Grammatura	ISO 536	g/m ²	80	90	100	120	160	250	300	±5%
Thickness / Spessore	ISO 534	µm	98	110	123	147	196	282	336	±5%
Bulk / Mano	ISO 534	cm ² /g	1,23	1,22	1,23	1,23	1,23	1,13	1,12	-
Whiteness / Bianco CIE	ISO 11475	%	94	94	94	94	94	94	94	±3
Opacity	ISO 2471	%	88	89	90	91	94	-	-	>
Cobb 60 sec FELT SIDE	ISO 535	g/m ²	30	30	30	30	35	35	35	±5
Cobb 60 sec WIRE SIDE	ISO 535	g/m ²	30	30	30	30	35	35	35	±5
Roughness/Liscio Bendtsen FELT SIDE	ISO 8791-2	ml/min	160	160	160	160	160	130	130	±50
Roughness/Liscio Bendtsen WIRE SIDE	ISO 8791-2	ml/min	160	160	160	160	160	130	130	±50
Absolute Humidity	ISO 287	%	5,2	5,2	5,8	5,8	5,8	6,5	6,5	±1

Controllo Qualità / Quality Control

M. Scapin