

# ClairRough

Technische Informationen							
Weight (g/m <sup>2</sup> ) ISO 536	<b>100</b>	<b>120</b>	<b>150</b>	<b>200</b>	<b>240</b>	<b>300</b>	<b>400</b>
Thickness (µm) ISO 534	152	180	220	290	345	416	550
Bulk (cm <sup>3</sup> /g) ISO 534	1.52	1.50	1.47	1.45	1.44	1.39	1.38
ISO Brightness (%) ISO 2470-2	116	116	116	116	116	116	116
CIE Brightness (%) ISO 11475	171	171	171	171	171	171	171
Bendtsen roughness (ml/min) ISO 8791-2	450	450	450	450	450	450	450
Absolute humidity (%H <sub>2</sub> O) ISO 20287	5.3	5.3	5.3	6.0	6.0	6.0	6.0
Relative humidity (% in the air)	40	40	40	45	45	45	45
Opacity (%) ISO 2471	96,5	97,5	98,5	99	>99	>99	>99
Formation index (Index on 120)	99	99	99	100	100	100	100

## Instructions of Manufacturer / Herstellerangaben

The Manufacturer is responsible for the validity of facts and figures.  
Der Hersteller ist für die Richtigkeit und Einhaltung der Angaben verantwortlich.

## Certificates and Labels / Zertifikate und Labels

FSC® certified, ECF Elemental chlorine free, BIR XXXVI certified



The mark of  
responsible forestry



BfR XXXVI



Certified