



Lessebo Design[®]

Product sheet

Grammage	Thickness	Bulk	Roughness Bendtsen	Whiteness Bright	Whiteness White	Whiteness * Natural	Whiteness * Ivory	Opacity
g/m ²	µm	cm ³ /g	ml/min	CIE	CIE	CIE	CIE	%
70	90	1,29	250	158	148	80	60	91
80	105	1,31	250	158	148	80	60	92
90	120	1,33	250	158	148	80	60	93
100	130	1,30	250	158	148	80	60	94
115	150	1,30	250	158	148	80	60	95
130	165	1,27	250	158	148	80	60	96
150	195	1,30	300	158	148	80	60	97
170	215	1,26	300	158	148	80	60	>97
200	250	1,25	300	158	148	80	60	>97
240	300	1,25	300	158	148	80	60	>97
270	330	1,22	300	158	148	80	60	>97
300	366	1,22	300	158	148	80	60	>97
350	430	1,23	300	158	148	80	60	>97
440	535	1,22	300	158	148	80	60	>97

* Natural and Ivory are manufactured without OBA



LESSEBO PAPER