

ICON Classic smooth white

Technische Informationen											
Grammatur / Weight (g/m ²) ISO 536	80	90	100	120	150	200	250	300	350	400	450
Dicke / Thickness (µm) ISO 534	99	111	123	155	195	240	307	370	415	485	545
Spez. Volumen / Spec. Volume (cm ³ /g) ISO 534	1,24	1,23	1,23	1,30	1,30	1,20	1,20	1,20	1,20	1,20	1,20
Glätte / Bekk (s) ISO 5627	25	25	25	15	15	15	15	15	15	15	15
Opazität / Opacity (%) ISO 2471	82	85	86	92	94	97	98	98,5	99	99	99
CIE Weiße / Whiteness (%) ISO 11475	139,5	139,5	139,5	139,5	139,5	139,5	139,5	139,5	139,5	139,5	139,5
Dennison Wachstest TAPPI T459	18	18	18	18	18	18	18	18	18	18	18
Berstwiderstand (kPa) ISO 2758	350	400	420	430	470	580	600	600	980	1050	1100
Abs. Feuchtigkeit / Abs. humidity (% H ₂ O) ISO 20287	7,90	7,90	7,90	7,90	7,90	7,90	7,90	7,90	7,90	7,90	7,90

ICON Classic smooth high white

Technische Informationen											
Grammatur / Weight (g/m ²) ISO 536	80	90	100	120	150	200	250	300	350	400	450
Dicke / Thickness (µm) ISO 534	99	111	123	155	195	240	307	370	415	485	545
Spez. Volumen / Spec. Volume (cm ³ /g) ISO 534	1,24	1,23	1,23	1,30	1,30	1,20	1,20	1,20	1,20	1,20	1,20
Glätte / Bekk (s) ISO 5627	25	25	25	15	15	15	15	15	15	15	15
Opazität / Opacity (%) ISO 2471	88	90	92	96	98	99	99	99	99,5	99,5	99,5
CIE Weiße / Whiteness (%) ISO 11475	168	168	168	168	168	168	168	168	168	168	168
Dennison Wachstest TAPPI T459	18	18	18	18	18	18	18	18	18	18	18
Berstwiderstand (kPa) ISO 2758	350	400	420	430	470	580	600	600	980	1050	1100
Abs. Feuchtigkeit / Abs. humidity (% H ₂ O) ISO 20287	7,90	7,90	7,90	7,90	7,90	7,90	7,90	7,90	7,90	7,90	7,90

Ziel-Produktionswerte Stand Dezember 2024.
Änderungen vorbehalten

