

CLASSIC
RECYCLING PAPER 80gsm – PERMANENT –
KRAFT 85 GSM
Forest Stewardship Council® FSC-C107414

Issue: 20/02/2020
 Last modification:-
 Revision: 0
 page 1/1

GENERAL PRODUCT CHARACTERISTICS

Total weight	183 gsm ± 5%	ISO 536
Total caliper	204 µm ± 5%	ISO 534

FACE

Recycled uncoated, environmental paper, 100% from recycled fibre (Post Consumer Waste)

Substance	80 gsm ± 3	ISO 536
Caliper	104µm ± 3	ISO 534
White CIE	112 CIE	ISO 11475
White UV	88%	ISO 2470

ADHESIVE

Water emulsion acrylic based permanent type, for application on a wide variety of surfaces such as paper, glass, steel

Peel adhesion	15.7/inch ± 2	FINAT1
Shear test	4h ± 2	FINAT8
Quick stick	13.7 N/inch ± 4	FINAT9
Min. application temp.	+5°C /+40°C	
Service temp. Range	-15°C/+80°C	

BACKING

One-side coated white kraft, solventless silicon coated

Substance	85 gsm ± 3	ISO 536
Caliper	87 µm ± 5	ISO 534

SAFETY REGULATIONS

The self-adhesive complex is Forest Stewardship Council® FSC-C107414 certified

- Face: EU Ecolabel certified, Austrian Ecolabel in conformity with the Standard EN12281, DIN 6738 and ISO 20494
- Adhesive coating and backing: meet the EU Standard EN71-3:2013 "Safety of Toys" - Migration of certain elements

APPLICATIONS

For labeling on recycled substrates, when an environmentally-conscious image is required

Trials are recommended, by the purchaser, on the intended substrates, prior to use, for product suitability.

PRINTABILITY

Face: good printing results by all common print processes, particularly suitable for offset printing.

Backing: good printing results by all common print processes, in one or more colors.

ON REQUEST

- Splits on the release paper, standard spacing 38mm or customized.

SHELF LIFE AND USE

One (1) year from delivery date when stored at the following conditions:

- Temperature +5°C/+35°C
- Relative Humidity 45% - 60%
- Store in a cool dry place
- Store away from heaters or direct sunlight or rain
- Keep the sheets flat, the reels piled
- Store in the original packaging, remove packaging just before use
- Material to be acclimatized at least 24 hrs to ambient conditions